

SCHEDA TECNICA TAGLIO LASER ACCIAIO AL CARBONIO (FERRO)

Cavallini Laser Tech - Modena

ACCIAI PER IMPIEGO STRUTTURALE

EUROPE				GERMANY	FRANCE	ITALY	BELGIUM	SWEDEN	U.K.	CANADA	CHINA	JAPAN		INTERNAT.
EN	EN 1.0025	DIS.	EN	DIN	NFA	UNI	NBN21-		BS	CSAG40-	GB	JIS	JIS	ISO630
1.0025-2	(90)	NE	1.0113-2	171.00	35 501	7070	1.01	SS14	4360	21	700/ GB-T 1591	31.01	31.06	
1.0037	Fe 360 B			St 37-2	E 24-2	Fe 360 B	AE 235-B				Q 235 A			Fe 31.0
1.0036	Fe 360 B	FU		Ust 37-2							Q 235 B			
1.0038	Fe 360 B	FN		RSt 37-2		Fe 360		13:11:00	40 (A) B	230 G	Q 235 B	SS400	SM400A	Fe 360 B
1.0114	Fe 360 C	FN			E 24-3	Fe 360 C	AE 235-C	13:12:00	40 C	Q 235 C			SM400B	Fe 360 C
1.0044	Fe 430 B	FN		St 44-2	E 28-2	Fe 360 B	AE 255-B	14:12:00	43 (A) B	260W,WT	Q 275 Z			Fe 430 B
1.0143	Fe 430 C	FN		St 44-3 U	E 28-3	Fe 430 C	AE 255-C		43 C		Q 275			Fe 430 C
1.0143	Fe 430 D1	FF	S 275N	St 44-3 N	E 28-4	Fe 430 D	AE 255-D	14:14:00	AE43 D		Q 275			Fe 430 D
1.0145	Fe 430 D2	FF	S 275N				AE 255-DD	14:14:00	43 EE		Q 275			
1.0045	Fe 510 B	FN			E 36-2	Fe 51.0 B	AE 355-B	21:32:01	50 B	350 W, WT	Q 345 C	SS490	SM490A	Fe 51.0 B
1.0553	Fe 510 C	FN		St 52-3 U	E 36-3	Fe 51.0 C	AE 335-C	21:34:01	50 C		16 Mn		SS490B	Fe 51.0 C
1.0570	Fe 510 D1	FF	S 355 N	St 52-3 N		Fe 51.0 D	AE 355-D	21:35:01	50 D				SS490C	Fe 51.0 D
1.0577	Fe 510 D2	FF	S 355 NL					26:42:00			Q 345 D		SS490YA	A 656
1.0595	Fe 510 DD1	FF			E 36-4	Fe 51.0 DD	AE 355-DD	26:44:11	50 DD				SS490YB	
1.0596	Fe 510 DD2	FF							50 EE				SM520B	